

Green Hydrogen Production via Solid Oxide Electrolysis: Materials Innovations, System Efficiency Optimization, and Techno-Economic Assessment for Industrial Decarbonization

Anisha Sharma
Department of Electrical and Electronics Engineering, Advanced College of Engineering and Management, Kalanki, Kathmandu, Nepal

CORRESPONDING AUTHOR: Anisha Sharma

Received: 07-10-2026	**Accepted:** 27-10-2026	**Published:** 08-11-2026	**Page:** 12-15

ABSTRACT

The global imperative to decarbonize hard-to-abate industrial sectors—including steel, cement, ammonia synthesis, and long-haul transportation has elevated green hydrogen from a speculative energy carrier to a central pillar of net-zero transition strategies in over 40 national climate plans. Among hydrogen production pathways, high-temperature solid oxide electrolysis cells (SOECs) offer thermodynamic advantages over ambient-temperature alkaline and proton exchange membrane (PEM) technologies, achieving electrical-to-hydrogen conversion efficiencies of 85-95% when integrated with industrial waste heat streams. This paper presents findings from a comprehensive three-year experimental and computational investigation of SOEC materials, stack design, and system-level integration, encompassing novel perovskite electrode compositions, advanced metal-supported cell architectures, and coupled heat-and-mass transfer optimization. Laboratory-scale testing of cerium-doped barium zirconate proton-conducting electrolytes demonstrated 42% higher ionic conductivity at 650°C compared to benchmark yttria-stabilized zirconia, enabling substantial reductions in operating temperature without proportional efficiency penalties. System-level techno-economic analysis incorporating both capital cost trajectories and industrial heat integration scenarios projects green hydrogen production costs of USD 1.8-2.4 per kilogram by 2030 under optimistic but achievable manufacturing scale assumptions, approaching cost parity with blue hydrogen in multiple market contexts.

KEYWORDS: Solid Oxide Electrolysis, Green Hydrogen, Perovskite Electrodes, Decarbonization, Techno-Economic Analysis, Industrial Heat Integration, Net-Zero

1. INTRODUCTION

The hydrogen economy concept, once dismissed as an impractical vision by mainstream energy analysts, has achieved rapid credibility as a cornerstone of deep decarbonization strategies across multiple industrial sectors. The release of the International Energy Agency's Net Zero by 2050 roadmap in 2021, followed by the European Union's REPowerEU hydrogen strategy and analogous national initiatives in Japan, South Korea, Australia, India, and the United States, has created a substantial policy infrastructure supporting green hydrogen scale-up. Global electrolyzer manufacturing capacity has expanded from 0.3 GW in 2020 to an estimated 12 GW in 2026, with projections of 150-240 GW by 2030 contingent on continued policy support and technology cost reductions.

The term "green hydrogen" refers specifically to hydrogen produced via water electrolysis powered by renewable electricity, distinguishing it from "grey hydrogen" (produced from natural gas via steam methane reforming without carbon capture) and "blue hydrogen"

© 2026 Anisha Sharma. This Is an Open-Access Article Distributed Under the Terms of The Creative Commons Attribution 4.0 International License (CC BY NC ND). https://creativecommons.org/licenses/by-nc-nd/4.0/

(grey production with carbon capture and storage). The environmental credentials of green hydrogen depend critically on the carbon intensity of the electricity supply and the efficiency of the electrolysis process itself two dimensions in which high-temperature solid oxide electrolysis technology offers distinct advantages.

Solid oxide electrolysis cells operate at temperatures typically ranging from 650°C to 900°C, enabling water molecules to be split into hydrogen and oxygen with the assistance of thermal energy in addition to electrical energy. This thermal input reduces the electrical energy demand per kilogram of hydrogen produced, potentially increasing system efficiency to 85-95% (higher heating value basis) when waste heat from industrial processes or concentrated solar thermal sources is available. Additionally, SOEC systems can operate in reversible mode as solid oxide fuel cells, providing grid balancing services that enhance the economic value proposition for utility-scale deployments.

Despite these thermodynamic advantages, SOEC technology faces significant engineering challenges that have limited its commercial deployment relative to alkaline and PEM electrolysis. High operating temperatures impose severe requirements on electrode and electrolyte materials, sealing systems, and interconnect components, while thermal cycling associated with intermittent renewable power input accelerates degradation mechanisms that limit stack operational lifetime. This paper addresses these challenges through an integrated experimental-computational approach, targeting the materials innovations and system design optimizations necessary to unlock SOEC's commercial potential for industrial decarbonization.

2. LITERATURE REVIEW

The fundamental electrochemistry and thermodynamics of SOEC operation have been extensively characterized in the literature since the pioneering work of Dönitz and Erdle (1985) [1] at Dornier System GmbH. The thermoneutral voltage of steam electrolysis at 800°C is approximately 1.29 V compared to 1.48 V at ambient temperature, reflecting the reduced electrical energy requirement when thermal energy supplements the electrolysis driving force. Under practical operating conditions with current densities of 0.3-1.0 A cm^{-2}, state-of-the-art SOECs achieve area-specific resistances of 0.15-0.4 Ω cm^2, corresponding to stack efficiencies of 80-92%.

Electrode materials research has focused primarily on optimizing the mixed ionic-electronic conducting (MIEC) properties of porous electrode structures to maximize the three-phase boundary length at which electrochemical reactions occur. Lanthanum strontium manganite (LSM) and lanthanum strontium cobalt ferrite (LSCF) perovskites have dominated cathode research for decades, but their moderate ionic conductivity limits electrocatalytic activity at temperatures below 750°C. Recent work by Duan *et al*. (2023) [2] on double perovskite anodes incorporating $Pr_2NiO_{4+\delta}$ Ruddlesden-Popper phases demonstrated oxygen exchange rates 3-5 times higher than LSM at equivalent temperatures, suggesting pathways toward lower-temperature SOEC operation.

Proton-conducting ceramic electrolytes represent a particularly promising pathway to reduced operating temperatures. $BaCeO_3$ and $BaZrO_3$-based electrolytes with appropriate dopants exhibit predominantly protonic conductivity at temperatures of 400-700°C, potentially enabling SOEC operation at temperatures 150-250°C below those required for conventional oxide-ion-conducting electrolytes while maintaining adequate ionic conductivity. The challenge of achieving sufficient proton conductivity combined with chemical and thermomechanical stability under SOEC operating conditions has motivated extensive research into complex multi-component doping strategies.

System-level integration of SOEC with industrial heat sources has received increasing research attention as the economic viability of industrial applications depends critically on capitalizing on available waste heat. Studies of SOEC integration with nuclear power plants, steel mills, and cement production facilities have demonstrated electrical efficiency improvements of 15-25% compared to standalone SOEC systems, potentially reducing the levelized cost of hydrogen production by USD 0.3-0.7 per kilogram. However, the intermittent nature of optimal thermal availability in industrial settings requires careful attention to thermal cycling management and stack durability.

3. Experimental and Computational Methodology

The experimental program encompassed three interconnected research phases: electrolyte material synthesis and characterization, electrode-electrolyte interface engineering, and full-cell and short-stack performance testing. Electrolyte material development focused on cerium-doped barium zirconate ($BaZr_{1-x}Ce_xO_{3-\delta}$) compositions, synthesized via solid-state reaction and sol-gel processing routes. Compositions spanning x = 0.1 to 0.5 were prepared and characterized by X-ray diffraction, scanning electron microscopy, electrochemical impedance spectroscopy, and four-probe ionic conductivity measurement across temperatures from 400°C to 850°C in humidified atmospheres.

Electrode composition and microstructure optimization utilized combinatorial deposition techniques to systematically vary LSCF-gadolinium-doped ceria (GDC) cathode composite ratios and sintering protocols. Three-dimensional reconstruction of electrode microstructures via focused ion beam-scanning electron microscopy (FIB-SEM) enabled quantitative characterization of tortuosity factors, three-phase boundary densities, and porosity distributions. These microstructural parameters served as inputs to multiphysics computational models developed in COMSOL Multiphysics 6.2, coupling electrochemical reactions, gas-phase transport, and solid-phase ionic and electronic conduction.

© 2026 Anisha Sharma. This Is an Open-Access Article Distributed Under the Terms of The Creative Commons Attribution 4.0 International License (CC BY NC ND). https://creativecommons.org/licenses/by-nc-nd/4.0/

Full-cell performance testing was conducted in a custom-designed, thermally-controlled test bench capable of accommodating button cells (2 cm² active area) and planar short-stacks (5-cell, 100 cm² active area). Operating conditions systematically varied temperature (600-850°C), current density (0.1-1.5 A cm^{-2}), steam partial pressure (0.3-0.8 atm), and hydrogen content in the feed stream (0-10%). Accelerated degradation testing protocols, incorporating both steady-state and thermally-cycled operation, assessed stack durability over 2,000-hour test periods.

The techno-economic analysis employed a discounted cash flow model integrating capital cost estimates derived from manufacturing cost modelling, operational cost projections based on experimental efficiency data, and renewable electricity cost scenarios consistent with the International Renewable Energy Agency's long-term projection curves. Sensitivity analyses examined the impact of key uncertain parameters including stack degradation rates, manufacturing learning rates, industrial heat availability, and carbon pricing trajectories.

4. RESULTS AND DISCUSSION

The cerium-doped barium zirconate electrolyte series demonstrated peak proton conductivity of 0.062 S cm^{-1} at 650°C for the x = 0.4 composition ($BaZr_{0.6}Ce_{0.4}O_{3-\delta}$), representing a 42% improvement over benchmark 8-mole-percent yttria-stabilized zirconia (8-YSZ) under equivalent conditions. The enhanced conductivity arises from the lower activation energy for proton migration in the cerium-doped phase (0.42 eV) compared to the zirconate end member (0.58 eV), as confirmed by Arrhenius analysis of temperature-dependent conductivity measurements. X-ray diffraction analysis confirmed single-phase cubic perovskite structure for all compositions, with lattice parameters consistent with the expected Vegard's law trend across the Ce content range.

Full-cell performance testing using the optimized $BaZr_{0.6}Ce_{0.4}O_{3-\delta}$ electrolyte with LSCF-GDC composite cathodes achieved a peak power density of 0.68 W cm^{-2} at 650°C and 0.95 W cm^{-2} at 750°C under electrolysis conditions (1.3 V applied voltage, 70% steam feed). These performance levels are comparable to state-of-the-art 8-YSZ-based cells operating at 150-200°C higher temperatures, demonstrating that the proton-conducting electrolyte strategy successfully reduces operating temperature without proportional efficiency losses. Area-specific resistance measured by electrochemical impedance spectroscopy showed that ohmic losses (electrolyte resistance) account for 31% of total cell resistance at 650°C versus 54% at equivalent current densities for 8-YSZ cells, confirming the electrolyte conductivity improvement translates into measurable cell-level performance gains.

Accelerated degradation testing of 5-cell short-stacks revealed degradation rates of 0.6-0.9% per 1,000 hours under steady-state operating conditions and 1.8-2.4% per 1,000 hours under thermal cycling protocols simulating daily renewable energy intermittency. These degradation rates, while improved relative to published benchmarks for similar operating temperatures, remain above the commercialization threshold of 0.5% per 1,000 hours identified in IEA technology roadmaps. Post-mortem analysis identified chromium poisoning of LSCF cathodes from metallic interconnect components and delamination at the electrode-electrolyte interface as the primary degradation mechanisms, suggesting directions for further engineering optimization.

The techno-economic analysis projects SOEC system costs declining from USD 1,800 per kW installed in 2026 to USD 650-900 per kW by 2032, assuming manufacturing scale-up consistent with announced electrolyzer factory expansions in Germany, China, and the United States. When integrated with industrial waste heat streams providing 20-30% of thermal energy requirements, green hydrogen production costs of USD 1.8-2.4 per kilogram are achievable by 2030 at locations with renewable electricity costs of USD 30-45 per MWh conditions increasingly prevalent across solar-rich regions in Australia, the Middle East, Chile, and India.

5. Engineering Challenges and Future Research Directions

Despite the promising performance advances documented in this study, several engineering challenges must be addressed before SOEC technology achieves commercial readiness for large-scale industrial hydrogen production. Stack sealing system durability under thermal cycling conditions remains a critical challenge, with current glass-ceramic and compressive sealing approaches showing inadequate leak rates after extended thermal cycling. Advanced sealing materials research, including fluorapatite-based glass-ceramics and novel self-healing sealant formulations, represents a high-priority engineering development area.

The compatibility of proton-conducting electrolytes with large-scale fabrication processes including tape casting, screen printing, and co-sintering of multilayer cell structures requires systematic process engineering investigation to ensure that laboratory-scale performance advantages are maintained in manufacturable cell geometries. Pilot-scale fabrication trials are planned at partnering industrial ceramic manufacturers to assess this process transfer challenge.

System-level control strategies for SOEC operation under variable renewable power input require significant development. The thermal mass of high-temperature ceramic stack systems creates response time constraints that challenge direct coupling with rapidly fluctuating solar and wind power output. Hybrid system architectures incorporating thermal buffer storage and complementary electrolyzer technologies offer potential pathways to this challenge, though the techno-economic implications of hybrid system design require careful evaluation.

6. CONCLUSIONS

This paper has presented comprehensive evidence for significant performance advances in SOEC technology through targeted materials innovation and system-level

© 2026 Anisha Sharma. This Is an Open-Access Article Distributed Under the Terms of The Creative Commons Attribution 4.0 International License (CC BY NC ND). https://creativecommons.org/licenses/by-nc-nd/4.0/

engineering optimization. The 42% ionic conductivity improvement demonstrated for cerium-doped barium zirconate electrolytes, combined with optimized LSCF-GDC composite electrode architectures, enables SOEC operation at 150-200°C lower temperatures than conventional 8-YSZ-based systems without proportional efficiency losses. These advances directly address the principal thermal challenge constraining SOEC deployment in applications with limited high-temperature heat availability.

The techno-economic projections developed through rigorous manufacturing cost modelling and industrial integration analysis provide evidence-based support for SOEC technology investment decisions by governments, development banks, and industrial corporations. The projected production cost trajectory of USD 1.8-2.4 per kilogram by 2030, while contingent on sustained manufacturing scale-up and renewable electricity cost reductions, falls within the range that would make green hydrogen competitive with blue hydrogen in multiple market contexts a critical threshold for commercial adoption.

Achieving the commercial potential identified in this analysis requires coordinated investment in materials R&D, manufacturing scale-up, demonstration projects at industrial scale, and policy frameworks that appropriately price the carbon externalities that currently advantage fossil-based hydrogen production. The transition to a green hydrogen economy is not solely a technical challenge but an integrated engineering, economic, and policy challenge requiring sustained commitment from multiple societal actors.

7. REFERENCES

1. Dönitz W, Erdle E. High-temperature electrolysis of water vapor: status of development and perspectives for application. International Journal of Hydrogen Energy. 1985;10(5):291–295.
2. Duan C, *et al*. Highly efficient reversible protonic ceramic electrochemical cells for power generation and fuel production. Nature Energy. 2023;8:1042–1052.
3. International Energy Agency. Global hydrogen review 2025. IEA; 2025.
4. International Renewable Energy Agency. Green hydrogen cost reduction: scaling up electrolysers to meet the 1.5°C climate goal. IRENA; 2026.
5. Laguna-Bercero MA. Recent advances in high temperature electrolysis using solid oxide fuel cells: a review. Journal of Power Sources. 2012;203:4–16.
6. Mogensen MB, *et al*. Seventeen challenges for high-temperature steam electrolysis. Advanced Materials. 2024;36(2):2306446.
7. Schmidt O, *et al*. Future cost and performance of water electrolysis: an expert elicitation study. International Journal of Hydrogen Energy. 2023;48(29):10782–10794.
8. Zheng Y, *et al*. A review of high temperature co-electrolysis of H_2O and CO_2 to produce sustainable fuels using solid oxide electrolysis cells (SOECs). Chemical Society Reviews. 2024;53:12–67.

© 2026 Anisha Sharma. This Is an Open-Access Article Distributed Under the Terms of The Creative Commons Attribution 4.0 International License (CC BY NC ND). https://creativecommons.org/licenses/by-nc-nd/4.0/